



## Technical Data Sheet BrazeTec 4900 A



TD BT 0017 E.02

### Inhalt

#### Standard

BrazeTec Standard  
ISO 3677

B-Ag49CuZnMnNi 670/690

#### Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]

Max. impurities [wt.-%]

Ag 49; Cu 27,5; Zn 20,5; Mn 2,5; Ni 0,5

Al 0,001; Bi 0,030; Cd 0,010; P 0,008; Pb 0,025; Si 0,05

0,3

#### Technical data

Melting range

approx. 670 - 690 °C

Working temperature

approx. 690 °C

Density

approx. 8,9 g/cm<sup>3</sup>

Shear strenght acc. DIN EN 12797

250 - 300 MPa (carbide/steel)

Electrical Conductivity

approx. 4,0

m/ Ωmm<sup>2</sup>

Operating temp. of brazed joint

max. 200 °C (without loss in strength)

#### Standard delivery forms\*

Wire:

1,0 - 1,5 - 2,0 mm Ø

Rods:

1,0 - 1,5 - 2,0 mm Ø, 500 mm length

Ribbon:

0,1/ 0,2/ 0,3/ 0,4 mm thickness and 70 mm width

Preforms:

rings, shaped parts, sections, stamped and shaped parts,  
shims, discs, perforated plates

\*Other delivery forms upon request

#### Applications

**BrazeTec 4900 A** is a low melting silver based brazing alloy with excellent flow characteristics. The brazing alloy is suitable for brazing of cemented carbides and materials which are difficult to wet, such as tungsten, molybdenum, tantalum and chromium. The reachable strength of the joint depends from the parent metals.

It can be used for brazing with flame or induction brazing procedures.

Typical applications are found e.g. in the tool industry.

Our information about our products and equipment as well as our systems and procedures are based on comprehensive research and application technological experience. We communicate these results, but take no liability for respective single contracts that are exceeding thereof. We reserve the right to make technical changes in the process of product development in spoken and written terms to the best of our knowledge. Only as an exception do we give guarantees for appearance and workmanship or durability that has been specifically documented in an individual contract. Furthermore, our application technology services are available at your convenience for more detailed consultation such as the involvement in solving manufacturing and application technology problems.

This does not however, release the user from their own responsibility for checking the input and recommendations we give for their own use prior to using that input or recommendation. This is especially applicable for foreign deliveries. This also applies to the trade mark rights of third parties, for applications and procedures that are not specifically given by us. In the event of damage or loss our liability is limited to indemnification of the same admeasurements as is foreseen in our general terms of sales and delivery in reference to deficiencies in quality.