



Technical Data Sheet BrazeTec 64/Cu



TD BT 0019 E.02

Inhalt

Standard

BrazeTec Standard
ISO 3677

B-Ag64CuInMnNi 730/780

Nominal composition [wt.-%]

Permitted impurities max. [wt.-%]

Max. impurities [wt.-%]

(brazing alloy layer) Ag 64; Cu 26; Mn 2; Ni 2; In 6
Al 0,001; Bi 0,030; Cd 0,010; P 0,008; Pb 0,025; Si 0,05
0,3

Technical data

Melting range

Working temperature

Density

Shear strenght acc. DIN EN 12797

Operating temp. of brazed joint

approx. 730 - 780 °C

approx. 770 °C

approx. 9,6 g/cm³

150 - 300 MPa (carbide/steel)

max. 200 °C (without loss in strength)

Standard delivery forms*

Ribbon:

Preforms:

*Other delivery forms upon request

0,4 mm thickness and 70 mm width

discs, sections, shaped parts

Applications

BrazeTec 64/Cu is a low melting silver based brazing alloy with copper interlayer to compensate the internal stresses of the joint. The brazing alloy is suitable for brazing of cemented carbides to steel. The reachable strength of the joint depends from the parent metals.

BrazeTec 64/Cu will be used especially if parts are going to get a vacuum coating as e.g. TiN and therefore Zn-containing brazing alloys are not suitable.

It can be used for brazing with flame, with induction heating and in a furnace under protective atmospheres.

Our information about our products and equipment as well as our systems and procedures are based on comprehensive research and application technological experience. We communicate these results, but take no liability for respective single contracts that are exceeding thereof. We reserve the right to make technical changes in the process of product development in spoken and written terms to the best of our knowledge. Only as an exception do we give guarantees for appearance and workmanship or durability that has been specifically documented in an individual contract. Furthermore, our application technology services are available at your convenience for more detailed consultation such as the involvement in solving manufacturing and application technology problems.

This does not however, release the user from their own responsibility for checking the input and recommendations we give for their own use prior to using that input or recommendation. This is especially applicable for foreign deliveries. This also applies to the trade mark rights of third parties, for applications and procedures that are not specifically given by us. In the event of damage or loss our liability is limited to indemnification of the same admeasurements as is foreseen in our general terms of sales and delivery in reference to deficiencies in quality.