



Technical Data Sheet BrazeTec CST 600 TD



TD BT 1320 E.03

Inhalt

Solvent based brazing paste

BrazeTec CST 600 TD is especially developed for the copper-brass radiator brazing process (CuproBraze). It is mainly designed for the application by spraying techniques. The binder system is solvent based and ensures fast drying, good adhesion and a residue free burnout under protective atmosphere.

Standard

BrazeTec Standard CPO 600 (OKC 600, Patent US 5 378 294)

Nominal composition [wt.-%]

Permitted impurities max. [wt.-%] Cu Rest; Sn 15,5; P 5,0; Ni 4,0
Al 0,010; Bi 0,030; Cd 0,010; O 0,050; Pb 0,025;
Zn 0,050; Zn + Cd 0,050

Technical data

Melting range of brazing alloy	approx. 590 - 610 °C
Working temperature	approx. 650 °C
Metal content	> 80 wt.-%
Density of brazing paste	approx. 3,4 g/cm ³ (20 °C)
Grain size of brazing alloy powder	< 90 µm
Viscosity	18 ± 3,0 Pa s (Cone-Plate; 150 µm; D= 1/s; 20 °C)
Drying temperature	about 100 - 120 °C at workpiece
Cleaning agent	BrazeTec Cleaning Agent TD
Shelf life	min. 6 months, but only in the original sealed container at storage temperatures between +5 to +30°C stir well before use

Packaging

Standard 10; 25 kg

Applications

BrazeTec CST 600 TD can be applied on the brass tubes prior brazing manually with conventional spraying guns or automatically with spraying units. The tubes can then be dried at temperatures between 100 °C and 120 °C with standard drying processes (hot air, infrared). After drying the cores can be assembled.

The brazing process has to be carried out in protective atmosphere using nitrogen at a brazing temperature of about 650 °C depending on brazing furnace, furnace cycle, size of parts etc. The brazing time above 600 °C should be as short as possible and not longer than 4 minutes in case of brazing radiators to avoid critical tin-alloying of the thin fin material.

Our information about our products and equipment as well as our systems and procedures are based on comprehensive research and application technological experience. We communicate these results, but take no liability for respective single contracts that are exceeding thereof. We reserve the right to make technical changes in the process of product development in spoken and written terms to the best of our knowledge. Only as an exception do we give guarantees for appearance and workmanship or durability that has been specifically documented in an individual contract. Furthermore, our application technology services are available at your convenience for more detailed consultation such as the involvement in solving manufacturing and application technology problems.

This does not however, release the user from their own responsibility for checking the input and recommendations we give for their own use prior to using that input or recommendation. This is especially applicable for foreign deliveries. This also applies to

the trade mark rights of third parties, for applications and procedures that are not specifically given by us. In the event of damage or loss our liability is limited to indemnification of the same admeasurements as is foreseen in our general terms of sales and delivery in reference to deficiencies in quality.